

Boric Acid Premix Ramming mass

Technical Specifications of Rishi Minerals Quartz and Raw Material:

Silica	SiO ₂	98.5% min
Alumina	Al ₂ O ₃	0.4% max
Iron Oxide	Fe ₂ O ₃	0.015%

Boric Acid	H ₃ BO ₃	1.2%
------------	--------------------------------	------

Technical Specifications of Rishi Minerals Premix Silica Ramming Mass:

Product Name	Grain Size	Max. Operating Temperature	Yield or Bulk Density	Chemical Binder
Boric Acid Premix Silica Ramming Mass	0 to 7mm	1700°C	2.20 g/cm ³	H ₃ BO ₃ 1.2%

Installation method:

Dry Ram (Use of Pneumatic Vibrator recommended) on Hot Face (RED in picture)

Standard Packing:

50Kg ± 0.1Kg in new HDPE bags with PP liner.

Shelf life:

6 months (store in cool and dry condition)

Signed by Management,
Rishi Minerals and Ores India Pvt Ltd



Works:
 Plot No 25,
 Gollapuram Industrial
 Park, Hindupur Mandal,
 Hindupur – 515211,
 Anantpur District (AP)

Contact:
 +91 9900598866
 +91 9620060550
info@rishiminerals.in
www.rishiminerals.in