

Refractory for Tundish T-CAST

Chemical Specifications of Rishi Minerals T-CAST:

Silica	SiO ₂	98% ± 0.5%
Alumina	Al ₂ O ₃	0.2% max
Others	Additive Mix	Total 2.2%

Physical Specifications of Rishi Minerals T-CAST:

Product Name	Grain Size	Temp. Limit	Yield or Bulk Density	Appearance
Tundish Ramming Mix – T-CAST	0 to 6mm	1700 °C	2.20 g/cm ³	Grey in color

Installation method:

Dry Ram (Use of Manual Ramming recommended) on Hot Face (red in picture)
 Refer Installation Manual.

Standard Packing:

25Kg ± 0.1Kg in new PP bags with LDPE liner.

Shelf life:

6 months (store in cool and dry condition)



Signed by Management,
 Rishi Minerals and Ores India Pvt Ltd



Works:
 Plot No. 25,
 Gollapuram APIIC
 Industrial Estate,
 Hindupur Mandal,
 Andhra Pradesh

Contact:
 +91 9900598866
 +91 9620060550
info@rishiminerals.in
www.rishiminerals.in
www.rishiminerals.com

Office:
 101, Brigade Business
 Suites, 1st Block
 Jayanagar, Ashoka
 Pillar, Bengaluru,
 India- 560011